



AMERICAN COATINGS

AU Series

APPLICATION INFORMATION

Do not apply below freezing temperatures or humidities above 85 percent.

APPLICATION METHOD

Conventional or Airless spray preferred. If it is necessary to apply by roller, consult your American Representative.

MIXING

American AU Series products are two component products with a mixing ratio of 4 to 1. Mix part B urethane into part A using mechanical agitation.

CLEAN-UP AND THINNING

Clean all equipment immediately with American Coatings TH 600 thinner. If thinning is necessary thin with TH 317 or TH 319 thinner.

SPRAY EQUIPMENT

FOR AIRLESS SPRAY

Pump Ratio -----	30:1
Air Supply (in) -----	100 psi
Hose Diameter (ID) -----	1/4"
Hose Length (max) -----	100'
Tip Size -----	.013-.019
Atomization Pressure -----	2,400 psi

FOR CONVENTIONAL SPRAY

Spray Pot Dual Regulation
Air Gauges for Pot Pressure and Atomization Air

Air Supply (in) -----	100 psi
Material Hose (ID) -----	1/2"
Material Hose Length -----	50'
Air Hose (ID) -----	5/16"
Fluid Pressure (psi) -----	40 - 50
Fluid Tip Orifice Size (in) -----	.046 - .070

SAFETY INFORMATION

FOR PROFESSIONAL USE ONLY! WARNING! FLAMMABLE!

Keep away from sparks or flame. Contains polyisocyanate catalyst, acetate, and ketone solvents.

INDIVIDUALS WITH LUNG OR BREATHING PROBLEMS OR PRIOR REACTION TO ISOCYANATES MUST NOT BE EXPOSED TO VAPOR OR SPRAY MIST.

Do not breathe vapor or spray mist. Wear an appropriate, properly fitted respirator approved by NIOSH/MSHA while exposed. An airline respirator (TC 19C NIOSH/MSHA) may be appropriate where airborne monitoring demonstrates vapor levels below ten times the applicable exposure limits. Follow directions for respirator use. Do not get in eyes, on skin, or on clothing. Wash thoroughly after handling. Keep away from heat, sparks, and flame. Use only with adequate ventilation.

FIRST AID: If affected by inhalation of vapor or spray mist, remove to fresh air. If breathing difficulty persists or occurs later, consult a physician and have label information available. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and call a physician; for skin, wash thoroughly with soap and water. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with applicable regulations.

NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling contents may be harmful or fatal. The contents of this package must be blended with other components before the product can be used. Any mixture of components will have hazards of both components. Before opening the packages, read all warning labels.

Follow all precautions.

SHIPPING DATA

Proper Shipping Name -----	Paint Liquid
Hazard Class -----	Part A Flammable Liquid Part B Combustible Liquid

Flash Pt. °F SETA -----	81°F Part A 80°F Part B
-------------------------	----------------------------

UN No. ----- 1263

PACKAGING

WEIGHT VARIES WITH EACH COLOR

Shipping WT. -----	<u>AU Coating</u>	<u>AU Catalyst</u>
	Ones 7.5 - 9.0 #	Qt. 1.65#
	Fives 37.5 - 45.0 #	1 Gal. 8.5#



AMERICAN COATINGS

DISCLAIMER

The facts stated and the recommendations and suggestions herein are based upon experiments and supplier information believed to be reliable. No guarantee is made of their accuracy, however, and American Coatings ASSUMES NO LIABILITY FOR PRODUCT FAILURE OTHER THAN TO SUPPLY REPLACEMENT MATERIAL FOR PRODUCTS SHOWN TO BE DEFECTIVE WHEN DELIVERED OR TO REFUND THE PURCHASE PRICE. Except as stated, THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. AMERICAN COATINGS SHALL NOT BE LIABLE FOR SPECIAL, INCIDENTAL AND CONSEQUENTIAL DAMAGES. No statement contained herein shall be construed as an inducement to infringe existing patents or as an endorsement of specific manufacturers.

Revised 10/06