



AMERICAN COATINGS

AZ84

APPLICATION INFORMATION

Do not apply below 50° F or humidities above 85 percent.

APPLICATION METHOD

Brush, Airless, or Conventional Spray. If spraying, apply an even wet coat, using a crosshatch technique to ensure uniform coverage.

MIXING

Mix slowly using hand or mechanical agitation.

CLEAN-UP AND THINNING

Clean all equipment with American Coatings TH 600 or TH 620 Thinner immediately after use. AZ 84 may require up to 20% reduction.

SPRAY EQUIPMENT

FOR AIRLESS SPRAY

Use a 3.8" ID Material Hose
Suppliers -----Graco, DeVilbiss, Speed Flo
Fluid Pump ----- 30:1
Fluid Orifice Size, (in) ----- .013 - .021
Approximate Fluid Pressure (psi) ----- 2,200

FOR CONVENTIONAL SPRAY

Supplier	Fluid Tip	Fluid Needle	Air Cap
De Vilbiss	AV-601-E	MBC-444-E	AV-1239-2 AV-40-24
Binks # 18	66	65	66PA

Air Atomization And Pot Pressure:
Air to Gun ----- 60 – 70 psi
Air to Pot ----- 10 – 20 psi
Pot should be equipped with a mechanical agitator.

SAFETY INFORMATION

WARNING! FLAMMABLE

American Coatings AZ 84 is flammable. Keep away from heat, sparks or open flames. Avoid prolonged contact with skin and breathing of vapors or spray mist. Use with adequate ventilation. Use of filter type respirator is recommended.

SHIPPING DATA

Proper Shipping Name ----- Paint Liquid
Hazard Class----- Flammable Liquid

Flash Pt. °F SETA ----- 90° F

UN No.----- 1263

SHIPPING WEIGHT

1 Gallon -----16.8 lbs.
1 Quart ----- 4.10 lbs.

PACKAGING

1 Gallon ----- 4 one gallon cans per case
1 Quart ----- 6 one quart cans per case

DISCLAIMER

The facts stated and the recommendations and suggestions herein are based upon experiments and supplier information believed to be reliable. No guarantee is made of their accuracy, however, and American Coatings ASSUMES NO LIABILITY FOR PRODUCT FAILURE OTHER THAN TO SUPPLY REPLACEMENT MATERIAL FOR PRODUCTS SHOWN TO BE DEFECTIVE WHEN DELIVERED OR TO REFUND THE PURCHASE PRICE. Except as stated, THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. AMERICAN COATINGS SHALL NOT BE LIABLE FOR SPECIAL, INCIDENTAL AND CONSEQUENTIAL DAMAGES. No statement contained herein shall be construed as an inducement to infringe existing patents or as an endorsement of specific manufacturers.

Revised 10/06



AMERICAN COATINGS