



AMERICAN COATINGS

TL 20

APPLICATION INFORMATION

Do not apply if temperature is below 50°F and/or above 85% relative humidity.

APPLICATION METHOD

Airless spray preferred, but can be rolled, or brushed. See your American Coatings Representative for information on catalyst injection systems.

MIXING

Thoroughly mix part B (MEKP) into part A before application. Beware of short pot life.

CLEAN-UP AND THINNING

Thinning is not recommended. Clean up tools and equipment with Styrene or TH 660 thinner.

SPRAY EQUIPMENT

Pump Ratio ----- 30:1
Air Supply (in) ----- 100 psi
Hose Diameter (ID) ----- ¼”
Hose Length (max) ----- 75’
Tip Size ----- .027
Atomization Pressure (psi) ----- 2,400

SAFETY INFORMATION

WARNING! FLAMMABLE, HARMFUL IF INHALED, CAUSES IRRITATION

Keep away from heat, sparks or flame. Vapors may cause flash fire. Use with adequate ventilation. Do not breathe vapors or spray mist. Wear an appropriate, properly fitted respirator during and after application unless air monitoring demonstrates vapor/mist levels are below applicable limits. Avoid contact with vinyl ester resin. Contains styrene monomer.

SHIPPING DATA

Proper Shipping Name ----- Paint Liquid
Hazard Class----- Flammable Liquid
Flash Point °F SETA
Part A ----- 80°F
Part B ----- Oxidizer

UN No.----- 1263

PACKAGING

PART A
Fives ----- 52.50 lbs.
55 Gallon Drums ----- 590 lbs.

DISCLAIMER

The facts stated and the recommendations and suggestions herein are based upon experiments and supplier information believed to be reliable. No guarantee is made of their accuracy, however, and American Coatings ASSUMES NO LIABILITY FOR PRODUCT FAILURE OTHER THAN TO SUPPLY REPLACEMENT MATERIAL FOR PRODUCTS SHOWN TO BE DEFECTIVE WHEN DELIVERED OR TO REFUND THE PURCHASE PRICE. Except as stated, THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. AMERICAN COATINGS SHALL NOT BE LIABLE FOR SPECIAL, INCIDENTAL AND CONSEQUENTIAL DAMAGES. No statement contained herein shall be construed as an inducement to infringe existing patents or as an endorsement of specific manufacturers.



AMERICAN COATINGS